



Designation: A240/A240M – 17

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications¹

This standard is issued under the fixed designation A240/A240M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers chromium, chromium-nickel, and chromium-manganese-nickel stainless steel plate, sheet, and strip for pressure vessels and for general applications including architectural, building, construction, and aesthetic applications.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 This specification is expressed in both inch-pound and SI units. However, unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished in inch-pound units.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved Nov. 1, 2017. Published November 2017. Originally approved in 1940. Last previous edition approved in 2016 as A240/A240M – 16a. DOI: 10.1520/A0240_A0240M-17.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-240 in Section II of that Code.

2. Referenced Documents

2.1 ASTM Standards:³

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels

E112 Test Methods for Determining Average Grain Size

E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 SAE Standard:⁴

J 1086 Practice for Numbering Metals and Alloys (UNS)

3. General Requirements

3.1 The following requirements for orders for material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A480/A480M.

3.1.1 Definitions;

3.1.2 General requirements for delivery;

3.1.3 Ordering information;

3.1.4 Process;

3.1.5 Special tests;

3.1.6 Heat treatment;

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

*A Summary of Changes section appears at the end of this standard

- 3.1.7 Dimensions and permissible variations;
- 3.1.8 Workmanship, finish and appearance;
- 3.1.9 Number of tests/test methods;
- 3.1.10 Specimen preparation;
- 3.1.11 Retreatment;
- 3.1.12 Inspection;
- 3.1.13 Rejection and reheating;
- 3.1.14 Material test report;
- 3.1.15 Certification; and
- 3.1.16 Packaging, marking, and loading.

4. Chemical Composition

4.1 The steel shall conform to the requirements as to chemical composition specified in **Table 1** and shall conform to applicable requirements specified in Specification **A480/A480M**.

5. Mechanical Properties

5.1 The material shall conform to the mechanical properties specified in **Table 2**.

5.2 When specified by the purchaser, Charpy impact tests shall be performed in accordance with Supplementary Requirement S1.

5.3 When specified by the purchaser, 1 % offset yield strength shall be measured and reported in accordance with Supplementary Requirement S3.

6. Materials for High-Temperature Service

6.1 The austenitic *H* Types shall conform to an average grain size of ASTM No. 7 or coarser as measured by Test Methods **E112**.

6.2 Supplementary Requirement S2 shall be invoked when non-H grade austenitic stainless steels are ordered for ASME Code applications for service above 1000°F [540°C].

6.3 Grade S31060, unless otherwise specified in the purchase order, shall conform to an average grain size of ASTM No. 7 or coarser, as measured by Test Methods **E112**.

7. Keywords

7.1 architectural; building; chromium; chromium-nickel stainless steel; chromium-manganese-nickel stainless steel; construction; pressure vessels

TABLE 1 Chemical Composition Requirements, %^A

UNS Designation ^B	Type ^C	Carbon ^D	Manganese	Phosphorus	Austenitic (Chromium-Nickel)				Nickel	Molybdenum	Nitrogen	Copper	Other Elements ^{E, F}
					Sulfur	Silicon	Chromium	Chromium-Manganese-Nickel					
N08020	...	0.07	2.00	0.045	0.035	1.00	19.0-21.0	32.0-38.0	2.00-3.00	...	3.00-4.00	Cb 8xC min, 1.00 max	
N08367	...	0.030	2.00	0.040	0.030	1.00	20.0-22.0	23.5-25.5	6.0-7.0	0.18-0.25	0.75	...	
N08700	...	0.04	2.00	0.040	0.030	1.00	19.0-23.0	24.0-26.0	4.3-5.0	...	0.50	Cb 8xC min 0.40 max	
N08800	800 ^G	0.10	1.50	0.045	0.015	1.00	19.0-23.0	30.0-35.0	0.75	Fe ^H 39.5 min Al 0.15-0.60 Ti 0.15-0.60	
N08810	800H ^G	0.05-0.10	1.50	0.045	0.015	1.00	19.0-23.0	30.0-35.0	0.75	Fe ^H 39.5 min Al 0.15-0.60 Ti 0.15-0.60	
N08811	...	0.06-0.10	1.50	0.040	0.015	1.00	19.0-23.0	30.0-35.0	0.75	Fe ^H 39.5 min Ti 0.25-0.60 Al 0.25-0.60	
N08904	904L ^G	0.020	2.00	0.045	0.035	1.00	19.0-23.0	23.0-28.0	4.00-5.00	0.10	1.00-2.00	...	
N08925	...	0.020	1.00	0.045	0.030	0.50	19.0-21.0	24.0-26.0	6.00-7.00	0.10-0.20	0.80-1.50	...	
N08926	...	0.020	2.00	0.030	0.010	0.50	19.0-21.0	24.0-26.0	6.00-7.00	0.15-0.25	0.50-1.50	...	
S20100	201	0.15	5.50-7.50	0.060	0.030	1.00	16.0-18.0	3.5-5.5	...	0.25	
S20103	...	0.03	5.50-7.50	0.045	0.030	0.75	16.0-18.0	3.5-5.5	...	0.25	
S20153	...	0.03	6.40-7.50	0.045	0.015	0.75	16.0-17.5	4.0-5.0	...	0.10-0.25	1.00	...	
S20161	...	0.15	4.00-6.00	0.040	0.040	3.00-4.00	15.0-18.0	4.0-6.0	...	0.08-0.20	
S20200	202	0.15	7.50-10.00	0.060	0.030	1.00	17.0-19.0	4.0-6.0	...	0.25	
S20400	...	0.030	7.00-9.00	0.040	0.030	1.00	15.0-17.0	1.50-3.00	...	0.15-0.30	
S20431	...	0.12	5.00-7.00	0.045	0.030	1.00	17.0-18.0	2.0-4.0	...	0.10-0.25	1.50-3.50	...	
S20432	...	0.08	3.00-5.00	0.045	0.030	1.00	17.0-18.0	4.0-6.0	...	0.05-0.20	2.00-3.00	...	
S20433	...	0.08	5.50-7.50	0.045	0.030	1.00	17.0-18.0	3.5-5.5	...	0.10-0.25	1.50-3.50	...	
S20910	XM-19 ^J	0.06	4.00-6.00	0.040	0.030	0.75	20.5-23.5	11.5-13.5	1.50-3.00	0.20-0.40	...	Cb 0.10-0.30 V 0.10-0.30	
S21400	XM-31 ^J	0.12	14.00-16.00	0.045	0.030	0.30-1.00	17.0-18.5	1.00	...	0.35 min	
S21600	XM-17 ^J	0.08	7.50-9.00	0.045	0.030	0.75	17.5-22.0	5.0-7.0	2.00-3.00	0.25-0.50	
S21603	XM-18 ^J	0.03	7.50-9.00	0.045	0.030	0.75	17.5-22.0	5.0-7.0	2.00-3.00	0.25-0.50	
S21640	...	0.08	3.50-6.50	0.060	0.030	1.00	17.5-19.5	4.0-6.5	0.50-2.00	0.08-0.30	
S21800	...	0.10	7.00-9.00	0.060	0.030	3.5-4.5	16.0-18.0	8.0-9.0	...	0.08-0.18	...	Cb 0.10-1.00	
S21904	XM-11 ^J	0.04	8.00-10.00	0.060	0.030	0.75	19.0-21.5	5.5-7.5	...	0.15-0.40	
S24000	XM-29 ^J	0.08	11.50-14.50	0.060	0.030	0.75	17.0-19.0	2.3-3.7	...	0.20-0.40	
S30100	301	0.15	2.00	0.045	0.030	1.00	16.0-18.0	6.0-8.0	...	0.10	
S30103	301L ^G	0.03	2.00	0.045	0.030	1.00	16.0-18.0	6.0-8.0	...	0.20	
S30153	301LN ^G	0.03	2.00	0.045	0.030	1.00	16.0-18.0	6.0-8.0	...	0.07-0.20	
S30200	302	0.15	2.00	0.045	0.030	0.75	17.0-19.0	8.0-10.0	...	0.10	
S30400	304	0.07	2.00	0.045	0.030	0.75	17.5-19.5	8.0-10.5	...	0.10	
S30403	304L	0.030	2.00	0.045	0.030	0.75	17.5-19.5	8.0-12.0	...	0.10	
S30409	304H	0.04-0.10	2.00	0.045	0.030	0.75	18.0-20.0	8.0-10.5	
S30415	...	0.04-0.06	0.80	0.045	0.030	1.00-2.00	18.0-19.0	9.0-10.0	...	0.12-0.18	...	Ce 0.03-0.08	
S30435	...	0.08	2.00	0.045	0.030	1.00	16.0-18.0	7.0-9.0	1.50-3.00	...	
S30441	...	0.08	2.00	0.045	0.030	1.0-2.0	17.5-19.5	8.0-10.5	...	0.10	1.5-2.5	Cb 0.1-0.5 W 0.2-0.8	
S30451	304N	0.08	2.00	0.045	0.030	0.75	18.0-20.0	8.0-10.5	...	0.10-0.16	
S30452	XM-21 ^J	0.08	2.00	0.045	0.030	0.75	18.0-20.0	8.0-10.5	...	0.16-0.30	
S30453	304LN	0.030	2.00	0.045	0.030	0.75	18.0-20.0	8.0-12.0	...	0.10-0.16	
S30500	305	0.12	2.00	0.045	0.030	0.75	17.0-19.0	10.5-13.0	
S30530	...	0.08	2.00	0.045	0.030	0.50-2.50	17.0-20.5	8.5-11.5	0.75-1.50	...	0.75-3.50	...	
S30600	...	0.018	2.00	0.020	0.020	3.7-4.3	17.0-18.5	14.0-15.5	0.20	...	0.50	...	
S30616	...	0.020	1.50	0.030	0.015	3.9-4.7	16.5-18.5	13.0-15.5	0.50	...	0.40	Cb 0.30-0.70	
S30601	...	0.015	0.50-0.80	0.030	0.013	5.0-5.6	17.0-18.0	17.0-18.0	0.20	0.05	0.35	...	
S30615	...	0.05-0.24	2.00	0.030	0.030	3.2-4.0	17.0-19.5	13.5-16.0	Al 0.80-1.50	
S30815	...	0.05-0.10	0.80	0.040	0.030	1.40-2.00	20.0-22.0	10.0-12.0	...	0.14-0.20	...	Ce 0.03-0.08	
S30908	309S	0.08	2.00	0.045	0.030	0.75	22.0-24.0	12.0-15.0	



TABLE 1 Continued

UNS Designation ^B	Type ^C	Carbon ^D	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum	Nitrogen	Copper	Other Elements ^{E, F}
S30909	309H ^G	0.04-0.10	2.00	0.045	0.030	0.75	22.0-24.0	12.0-15.0	Cb 10xC min, 1.10 max
S30940	309Cb ^G	0.08	2.00	0.045	0.030	0.75	22.0-24.0	12.0-16.0	Cb 10xC min, 1.10 max
S30941	309HCb ^G	0.04-0.10	2.00	0.045	0.030	0.75	22.0-24.0	12.0-16.0	Cb 10xC min, 1.10 max
S31008	310S	0.08	2.00	0.045	0.030	1.50	24.0-26.0	19.0-22.0
S31009	310H ^G	0.04-0.10	2.00	0.045	0.030	0.75	24.0-26.0	19.0-22.0	Cb 10xC min, 1.10 max
S31040	310Cb ^G	0.08	2.00	0.045	0.030	1.50	24.0-26.0	19.0-22.0	Cb 10xC min, 1.10 max
S31041	310HCb ^G	0.04-0.10	2.00	0.045	0.030	0.75	24.0-26.0	19.0-22.0	Cb 10xC min, 1.10 max
S31050	310 MolN ^G	0.020	2.00	0.030	0.010	0.50	24.0-26.0	20.5-23.5	1.60-2.60	0.09-0.15	...	Ce + La
S31060	...	0.05-0.10	1.00	0.040	0.030	0.50	22.0-24.0	10.0-12.5	...	0.18-0.25	...	0.025-0.070
S31254	...	0.020	1.00	0.030	0.010	0.80	19.5-20.5	17.5-18.5	6.0-6.5	0.18-0.25	0.50-1.00	B 0.001-0.010
S31266	...	0.030	2.00-4.00	0.035	0.020	1.00	23.0-25.0	21.0-24.0	5.2-6.2	0.35-0.60	1.00-2.50	W 1.50-2.50
S31277	...	0.020	3.00	0.030	0.010	0.50	20.5-23.0	26.0-28.0	6.5-8.0	0.30-0.40	0.50-1.50	...
S31600	316	0.08	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	0.10
S31603	316L	0.030	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	0.10
S31609	316H	0.04-0.10	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	Ti 5 x (C + N)
S31635	316Ti ^G	0.08	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	0.10	...	min, 0.70 max
S31640	316Cb ^G	0.08	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	0.10	...	Cb 10 x C min, 1.10 max
S31651	316N	0.08	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	0.10-0.16
S31653	316LN	0.030	2.00	0.045	0.030	0.75	16.0-18.0	10.0-14.0	2.00-3.00	0.10-0.16
S31655	...	0.030	2.00	0.045	0.015	1.00	19.5-21.5	8.0-9.5	0.50-1.50	0.14-0.25	1.00	...
S31700	317	0.08	2.00	0.045	0.030	0.75	18.0-20.0	11.0-15.0	3.0-4.0	0.10
S31703	317L	0.030	2.00	0.045	0.030	0.75	18.0-20.0	11.0-15.0	3.0-4.0	0.10
S31725	317LM ^G	0.030	2.00	0.045	0.030	0.75	18.0-20.0	13.5-17.5	4.0-5.0	0.20
S31726	317LMN ^G	0.030	2.00	0.045	0.030	0.75	17.0-20.0	13.5-17.5	4.0-5.0	0.10-0.20
S31727	...	0.030	1.00	0.030	0.030	1.00	17.5-19.0	14.5-16.5	3.8-4.5	0.15-0.21	2.80-4.00	...
S31730	...	0.030	2.00	0.040	0.010	1.00	17.0-19.0	15.0-16.5	3.0-4.0	0.045	4.0-5.0	...
S31753	317LN ^G	0.030	2.00	0.045	0.030	0.75	18.0-20.0	11.0-15.0	3.0-4.0	0.10-0.22
S32050	...	0.030	1.50	0.035	0.020	1.00	22.0-24.0	20.0-23.0	6.0-6.8	0.21-0.32	0.40	...
S32053	...	0.030	1.00	0.030	0.010	1.00	22.0-24.0	24.0-26.0	5.0-6.0	0.17-0.22
S32100	321	0.08	2.00	0.045	0.030	0.75	17.0-19.0	9.0-12.0	...	0.10	...	Ti 5 x (C + N) min, 0.70 max
S32109	321H	0.04-0.10	2.00	0.045	0.030	0.75	17.0-19.0	9.0-12.0	min, 0.70 max
S32615	...	0.07	2.00	0.045	0.030	4.80-6.00	16.5-19.5	19.0-22.0	0.30-1.50	...	1.50-2.50	...
S32654	...	0.020	2.00-4.00	0.030	0.005	0.50	24.0-25.0	21.0-23.0	7.0-8.0	0.45-0.55	0.30-0.60	...
S33228	...	0.04-0.08	1.00	0.020	0.015	0.30	26.0-28.0	31.0-33.0	Ce 0.05-0.10
S33400	334 ^G	0.08	1.00	0.030	0.015	1.00	18.0-20.0	19.0-21.0	Cb 0.6-1.0
S33425	...	0.08	1.50	0.045	0.020	1.00	21.0-23.0	20.0-23.0	2.00-3.00	Al 0.025
S33550	...	0.04-0.10	1.50	0.040	0.030	1.00	25.0-28.0	16.5-20.0	...	0.18-0.25	...	Al 0.15-0.60
S34565	...	0.030	5.00-7.00	0.030	0.010	1.00	23.0-25.0	16.0-18.0	4.0-5.0	0.40-0.60	...	Ti 0.15-0.60
S34700	347	0.08	2.00	0.045	0.030	0.75	17.0-19.0	9.0-13.0	Ti 0.15-0.60
												Cb 0.05-0.15
												La + Ce
												0.025-0.070
												Cb 0.10
												Cb 10 x C min, 1.00 max



TABLE 1 Continued

UNS Designation ^B	Type ^C	Carbon ^D	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum	Nitrogen	Copper	Other Elements ^{E, F}
S34709	347H	0.04-0.10	2.00	0.045	0.030	0.75	17.0-19.0	9.0-13.0	Cb 8 x C min, 1.00 max
S34751	347LN	0.005-0.020	2.00	0.045	0.030	1.00	17.0-19.0	9.0-13.0	...	0.06-0.10	...	Cb 0.20-0.50, 15 x C min
S34800	348	0.08	2.00	0.045	0.030	0.75	17.0-19.0	9.0-13.0	(Cb + Ta) 10xC min, 1.00 max
S34809	348H	0.04-0.10	2.00	0.045	0.030	0.75	17.0-19.0	9.0-13.0	Ta 0.10
S35045	...	0.06-0.10	1.50	0.045	0.015	1.00	25.0-29.0	32.0-37.0	0.75	Co 0.20
S35115	...	0.030	1.00	0.045	0.015	0.50-1.50	23.0-25.0	19.0-22.0	1.50-2.50	0.20-0.30	...	Al 0.15-0.60
S35125	...	0.10	1.00-1.50	0.045	0.015	0.50	20.0-23.0	31.0-35.0	2.00-3.00	Ti 0.15-0.60
S35135	...	0.08	1.00	0.045	0.015	0.60-1.00	20.0-25.0	30.0-38.0	4.0-4.8	Cb 0.25-0.60
S35140	...	0.10	1.00-3.00	0.045	0.030	0.75	20.0-22.0	25.0-27.0	1.00-2.00	0.08-0.20	0.75	Ti 0.40-1.00
S35315	...	0.04-0.08	2.00	0.040	0.030	1.20-2.00	24.0-26.0	34.0-36.0	...	0.12-0.18	...	Cb 0.25-0.75
S38100	XM-15 ^V	0.08	2.00	0.030	0.030	1.50-2.50	17.0-19.0	17.5-18.5	Ce 0.03-0.10
S38815	...	0.030	2.00	0.040	0.020	5.50-6.50	13.0-15.0	15.0-17.0	0.75-1.50
Duplex (Austenitic-Ferritic)												
S31200	...	0.030	2.00	0.045	0.030	1.00	24.0-26.0	5.5-6.5	1.20-2.00	0.14-0.20
S31260	...	0.03	1.00	0.030	0.030	0.75	24.0-26.0	5.5-7.5	2.5-3.5	0.10-0.30	0.20-0.80	W 0.10-0.50
S31803	...	0.030	2.00	0.030	0.020	1.00	21.0-23.0	4.5-6.5	2.5-3.5	0.08-0.20
S32001	...	0.030	4.00-6.00	0.040	0.030	1.00	19.5-21.5	1.00-3.00	0.60	0.05-0.17	1.00	...
S32003	...	0.030	2.00	0.030	0.020	1.00	19.5-22.5	3.0-4.0	1.50-2.00	0.14-0.20
S32101	...	0.040	4.00-6.00	0.040	0.030	1.00	21.0-22.0	1.35-1.70	0.10-0.80	0.20-0.25	0.10-0.80	...
S32202	...	0.030	2.00	0.040	0.010	1.00	21.5-24.0	1.00-2.80	0.45	0.18-0.26
S32205	2205 ^G	0.030	2.00	0.030	0.020	1.00	22.0-23.0	4.5-6.5	3.0-3.5	0.14-0.20
S32304	2304 ^G	0.030	2.50	0.040	0.030	1.00	21.5-24.5	3.0-5.5	0.05-0.60	0.05-0.20	0.05-0.60	...
S32506	...	0.030	1.00	0.040	0.015	0.80	24.0-26.0	5.5-7.2	3.0-3.5	0.08-0.20	...	W 0.05-0.30
S32520	...	0.030	1.50	0.035	0.020	0.90	24.0-26.0	5.5-8.0	3.0-4.0	0.20-0.35
S32550	255 ^G	0.04	1.50	0.040	0.030	1.00	24.0-27.0	4.5-6.5	2.9-3.9	0.10-0.25	1.50-2.50	...
S32750	2507 ^{G, O}	0.030	1.20	0.035	0.020	0.80	24.0-26.0	6.0-8.0	3.0-5.0	0.24-0.32	0.50	...
S32760 ^K	...	0.030	1.00	0.030	0.010	1.00	24.0-26.0	6.0-8.0	3.0-4.0	0.20-0.30	0.50-1.00	W 0.50-1.00
S32808	...	0.030	1.10	0.030	0.010	0.50	27.0-27.9	7.0-8.2	0.80-1.2	0.30-0.40	...	W 2.10-2.50
S32900	329	0.08	1.00	0.040	0.030	0.75	23.0-28.0	2.0-5.00	1.00-2.00
S32906	...	0.030	0.80-1.50	0.030	0.030	0.80	28.0-30.0	5.8-7.5	1.50-2.60	0.30-0.40	0.80	...
S32950	...	0.030	2.00	0.035	0.010	0.60	26.0-29.0	3.5-5.2	1.00-2.50	0.15-0.35
S39274	...	0.030	1.00	0.030	0.020	0.80	24.0-26.0	6.0-8.0	2.5-3.5	0.24-0.32	0.20-0.80	W 1.50-2.50
S81921	...	0.030	2.00-4.00	0.040	0.030	1.00	19.0-22.0	2.0-4.0	1.00-2.00	0.14-0.20
S82011	...	0.030	2.00-3.00	0.040	0.020	1.00	20.5-23.5	1.0-2.0	0.10-1.00	0.15-0.27	0.50	...
S82012	...	0.05	2.00-4.00	0.040	0.005	0.80	19.0-20.5	0.8-1.5	0.10-0.60	0.16-0.26	1.00	...
S82013	...	0.060	2.50-3.50	0.040	0.030	0.90	19.5-22.0	0.5-1.5	...	0.20-0.30	0.20-1.20	...
S82031	...	0.05	2.50	0.040	0.005	0.80	19.0-22.0	2.0-4.0	0.60-1.40	0.14-0.24	1.00	...
S82121	...	0.035	1.00-2.50	0.040	0.010	1.00	21.0-23.0	2.0-4.0	0.30-1.30	0.15-0.25	0.20-1.20	...
S82122	...	0.030	2.0-4.0	0.040	0.020	0.75	20.5-21.5	1.5-2.5	0.60	0.15-0.20	0.50-1.50	...
S82441	...	0.030	2.50-4.00	0.035	0.005	0.70	23.0-25.0	3.0-4.5	1.00-2.00	0.20-0.30	0.10-0.80	...
Ferritic or Martensitic (Chromium)												
S32803	...	0.015	0.50	0.020	0.0035	0.55	28.0-29.0	3.0-4.0	1.80-2.50	0.020	...	Cb 12x(C+N) min, 0.15-0.50
S40300	403	0.15	1.00	0.040	0.030	0.50	11.5-13.0	0.60	...	(C+N) 0.030
S40500	405	0.08	1.00	0.040	0.030	1.00	11.5-14.5	0.60
S40900 ^L	409 ^L	0.08	1.00	0.040	0.030	1.00	11.5-14.5	0.60	Al 0.10-0.30



TABLE 1 Continued

UNS Designation ^B	Type ^C	Carbon ^D	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum	Nitrogen	Copper	Other Elements ^{E, F}
S40910	...	0.030	1.00	0.040	0.020	1.00	10.5–11.7	0.50	...	0.030	...	Ti 6x(C+N) min, 0.50 max; Cb 0.17
S40920	...	0.030	1.00	0.040	0.020	1.00	10.5–11.7	0.50	...	0.030	...	Ti 8x(C+N) min, Ti 0.15–0.50; Cb 0.10
S40930	...	0.030	1.00	0.040	0.020	1.00	10.5–11.7	0.50	...	0.030	...	(Ti+Cb) [0.08+8x(C+N)] min, 0.75 max;
S40945	...	0.030	1.00	0.040	0.030	1.00	10.5–11.7	0.50	...	0.030	...	Ti 0.05 min
S40975	...	0.030	1.00	0.040	0.030	1.00	10.5–11.7	0.50–1.00	...	0.030	...	Cb 0.18–0.40
S40977	...	0.030	1.50	0.040	0.015	1.00	10.5–12.5	0.30–1.00	...	0.030	...	Ti 0.05–0.20
S41000	410	0.08–0.15	1.00	0.040	0.030	1.00	11.5–13.5	0.75	Ti 6x(C+N) min, 0.75 max
S41003	...	0.030	1.50	0.040	0.030	1.00	10.5–12.5	1.50	...	0.030
S41008	410S	0.08	1.00	0.040	0.030	1.00	11.5–13.5	0.60
S41045	...	0.030	1.00	0.040	0.030	1.00	12.0–13.0	0.50	...	0.030	...	Cb 9x(C+N) min, 0.60 max
S41050	...	0.04	1.00	0.045	0.030	1.00	10.5–12.5	0.60–1.10	...	0.10
S41500 ^M	...	0.05	0.50–1.00	0.030	0.030	0.60	11.5–14.0	3.5–5.5	0.50–1.00
S42000	420	0.15 min	1.00	0.040	0.030	1.00	12.0–14.0	0.75	0.50
S42035	...	0.08	1.00	0.045	0.030	1.00	13.5–15.5	1.0–2.5	0.2–1.2	Ti 0.30–0.50
S42200	422	0.20–0.25	0.50–1.00	0.025	0.025	0.50	11.0–12.5	0.50–1.00	0.90–1.25	V 0.20–0.30, W 0.90–1.25
S42900	429 ^G	0.12	1.00	0.040	0.030	1.00	14.0–16.0
S43000	430	0.12	1.00	0.040	0.030	1.00	16.0–18.0	0.75	Ti [0.20+4(C+N)] min, 1.10 max; Al 0.15
S43035	439	0.030	1.00	0.040	0.030	1.00	17.0–19.0	0.50	...	0.030
S43037	...	0.030	1.00	0.040	0.030	1.00	16.0–19.0	Ti 0.10–1.00
S43100	431	0.20	1.00	0.040	0.030	1.00	15.0–17.0	1.25–2.50
S43400	434	0.12	1.00	0.040	0.030	1.00	16.0–18.0	...	0.75–1.25
S43600	436	0.12	1.00	0.040	0.030	1.00	16.0–18.0	...	0.75–1.25	Cb 5xC min, 0.80 max
S43932	...	0.030	1.00	0.040	0.030	1.00	17.0–19.0	0.50	...	0.030	...	(Ti+Cb) [0.20+4(C+N)] min, 0.75 max; Al 0.15
S43940	...	0.030	1.00	0.040	0.015	1.00	17.5–18.5	Ti 0.10–0.60 Cb [0.30+(3xC)] min
S44100	...	0.030	1.00	0.040	0.030	1.00	17.5–19.5	1.00	...	0.030	...	Ti 0.1–0.5 Cb [0.3 + (9xC)] min, 0.90 max
S44200	442	0.20	1.00	0.040	0.040	1.00	18.0–23.0	0.60
S44330	...	0.025	1.00	0.040	0.030	1.00	20.0–23.0	0.025	...	(Ti+Cb) 8x(C+N) min, 0.80 max
S44400	444	0.025	1.00	0.040	0.030	1.00	17.5–19.5	1.00	1.75–2.50	0.035	...	(Ti+Cb)[0.20+4(C+N)] min, 0.80 max
S44500	...	0.020	1.00	0.040	0.012	1.00	19.0–21.0	0.60	...	0.03	0.30–0.60	Cb 10x(C+N) min, 0.80 max
S44535	...	0.030	0.30–0.80	0.050	0.020	0.50	20.0–24.0	0.50	La 0.04–0.20, Ti 0.03–0.20, Al 0.50



TABLE 1 Continued

UNS Designation ^B	Type ^C	Carbon ^D	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum	Nitrogen	Copper	Other Elements ^{E, F}
S44536	...	0.015	1.00	0.040	0.030	1.00	20.0–23.0	0.5	...	0.015	...	(Ti+Cb) 8X(C+N)–0.8, Cb min 0.05 Al 0.1 W 1.0–3.0 Cb 0.2–1.0 Ti 0.02–0.20 La 0.04–0.20
S44537	...	0.030	0.8	0.050	0.006	0.1–0.6	20.0–24.0	0.5	...	0.04	0.5	Ti 0.20–1.00; Ti 7(C+N) min Cb 0.05–0.20 (Ni + Cu) 0.50 (Ti+Cb) [0.20+4(C+N)] min, 0.80 max
S44626	XM-33 ^V	0.06	0.75	0.040	0.020	0.75	25.0–27.0	0.50	0.75–1.50	0.04	0.20	...
S44627	XM-27 ^V	0.010 ^N	0.40	0.020	0.020	0.40	25.0–27.5	0.50	0.75–1.50	0.015 ^N	0.20	(Ti+Cb) 0.20 – 1.00, Ti + Cb 6X(C+N) min (C+N) 0.025 (Ti+Cb) min ≥8X(C+N) (Ti+Cb) 0.20–1.00, (Ti+Cb) 6X(C+N) min
S44635	...	0.025	1.00	0.040	0.030	0.75	24.5–26.0	3.5–4.5	3.5–4.5	0.035
S44600	446	0.20	1.50	0.040	0.030	1.00	23.0–27.0	0.75	...	0.25
S44660	...	0.030	1.00	0.040	0.030	1.00	25.0–28.0	1.0–3.5	3.0–4.0	0.040
S44700	...	0.010	0.30	0.025	0.020	0.20	28.0–30.0	0.15	3.5–4.2	0.020	0.15	(C+N) 0.025 (Ti+Cb) min
S44725	...	0.015	0.40	0.040	0.020	0.040	25.0–28.5	0.30	1.5–2.5	0.018
S44735	...	0.030	1.00	0.040	0.030	1.00	28.0–30.0	1.00	3.6–4.2	0.045
S44800	...	0.010	0.30	0.025	0.020	0.20	28.0–30.0	2.00–2.50	3.5–4.2	0.020	0.15	(C+N) 0.025 Ti 0.07–0.30
S46800	...	0.030	1.00	0.040	0.030	1.00	18.0–20.0	0.50	...	0.030	...	Cb 0.10–0.60 (Ti+Cb) [0.20+4(C+N)] min, 0.80 max

^A Maximum, unless range or minimum is indicated. Where ellipses (. . .) appear in this table, there is no requirement and the element need not be determined or reported.

^B Designation established in accordance with Practice E527 and SAE J 1086.

^C Unless otherwise indicated, a grade designation originally assigned by the American Iron and Steel Institute (AISI).

^D Carbon analysis shall be reported to nearest 0.01 % except for the low-carbon types, which shall be reported to nearest 0.001 %.

^E The terms Columbium (Cb) and Niobium (Nb) both relate to the same element.

^F When two minimums or two maximums are listed for a single type, as in the case of both a formula and an absolute value, the higher minimum or lower maximum shall apply.

^G Common name, not a trademark, widely used, not associated with any one producer.

^H Iron shall be determined arithmetically by difference of 100 minus the sum of the other specified elements.

^I (Al + Ti) 0.85–1.20.

^J Naming system developed and applied by ASTM.

^K Cr + 3.3 Mo + 16 N = 40 min.

^L S40900 (Type 409) has been replaced by S40910, S40920, and S40930. Unless otherwise specified in the ordering information, an order specifying S40900 or Type 409 shall be satisfied by any one of S40910, S40920, or S40930 at the option of the seller. Material meeting the requirements of S40910, S40920, or S40930, may at the option of the manufacturer be certified as S40900.

^M Plate version of CA-6NM.

^N Product (check or verification) analysis tolerance over the maximum limit for C and N in XM-27 shall be 0.002 %.

^O Cr + 3.3 Mo + 16 N = 41 min.



TABLE 2 Mechanical Test Requirements

UNS Designation	Type ^A	Tensile Strength, min		Yield Strength, ^B min		Elongation in 2 in. or 50 mm, min, %		Hardness, max ^C		Cold Bend ^D
		ksi	MPa	ksi	MPa	30 ^F	2 in. or 50 mm, min, %	Brinell, HBW	Rockwell	
N08020	...	80	550	35	240	30 ^F	217	95 HRBW	not required	
N08367	...	100	690	45	310	30	...	100 HRBW	not required	
N08700	...	95	655	45	310	30	241	...	not required	
N08800	800 ^F	80	550	35	240	30	192	90 HRBW	not required	
N08810	800H ^F	75	520	30 ^G	205 ^G	30 ^H	not required	
N08811	...	65	450	25 ^G	170 ^G	30	not required	
N08904	904L ^F	65	450	25	170	30	not required	
N08925	...	71	490	31	220	35	...	90 HRBW	not required	
N08926	...	87	600	43	295	40	not required	
N08926	...	94	650	43	295	35	not required	
S20100	201-1 ^J	75	515	38	260	40	217	95 HRBW	...	
S20100	201-2 ^J	95	655	45	310	40	241	100 HRBW	...	
S20103	201L ^F	95	655	38	260	40	217	95 HRBW	not required	
S20153	201LN ^F	95	655	45	310	45	241	100 HRBW	not required	
S20161	...	125	860	50	345	40	255	25 HRC	not required	
S20200	202	90	620	38	260	40	241	
S20400	...	95	655	48	330	35	241	100 HRBW	not required	
S20431	...	90	620	45	310	40	241	100 HRBW	not required	
S20432	...	75	515	30	205	40	201	92 HRBW	not required	
S20433	...	80	550	35	240	40	217	95 HRBW	not required	
S20910	XM-19 ^J	105	725	60	415	30	241	100 HRBW	not required	
S21600	Plate	100	690	55	380	35	241	100 HRBW	not required	
S21600	Sheet and Strip	100	690	60	415	40	241	100 HRBW	not required	
S21603	Plate	90	620	50	345	40	241	100 HRBW	not required	
S21603	Sheet and Strip	100	690	60	415	40	241	100 HRBW	not required	
S21640	Plate	90	620	50	345	40	241	100 HRBW	not required	
S21800	...	95	650	45	310	40	not required	
S21904	...	95	655	50	345	35	241	100 HRBW	not required	
S21904	Sheet and Strip	100	690	60	415	40	241	100 HRBW	not required	
S24000	Plate	90	620	50	345	45	241	100 HRBW	not required	
S24000	Sheet and Strip	100	690	60	415	40	241	100 HRBW	not required	
S30100	301	75	515	30	205	40	217	95 HRBW	not required	
S30103	301L ^F	80	550	32	220	45	241	100 HRBW	not required	
S30153	301LN ^F	80	550	35	240	45	241	100 HRBW	not required	
S30200	302	75	515	30	205	40	201	92 HRBW	not required	
S30400	304	75	515	30	205	40	201	92 HRBW	not required	
S30403	304L	70	485	25	170	40	201	92 HRBW	not required	
S30409	304H	75	515	30	205	40	201	92 HRBW	not required	
S30415	...	87	600	42	290	40	217	95 HRBW	not required	
S30435	...	65	450	23	155	45	187	90 HRBW	...	



TABLE 2 Continued

UNS Designation	Type ^A	Tensile Strength, min		Yield Strength, ^B min		Elongation in 2 in. or 50 mm, min, %	Hardness, max ^C		Cold Bend ^D	
		ksi	MPa	ksi	MPa		Brinell, HBW	Rockwell		
S30441	...	75	515	30	205	40	201	92 HRBW	not required	
S30451	304N	80	550	35	240	30	217	95 HRBW	not required	
S30452	XM-21 [✓]									
Sheet and Strip										
S30453	304LN	90	620	50	345	30	241	100 HRBW	not required	
S30500	305	85	585	40	275	30	241	100 HRBW	not required	
S30530	...	75	515	30	205	40	217	95 HRBW	not required	
S30530	...	70	485	25	170	40	183	88 HRBW	not required	
S30600	...	75	515	30	205	40	201	92 HRBW	not required	
S30616	...	78	540	35	240	40	
S30601	...	86	590	36	245	40	241	100 HRBW	not required	
S30615	...	78	540	37	255	30	not required	
S30615	...	90	620	40	275	35	217	95 HRBW	not required	
S30815	...									
S30908	309S	87	600	45	310	40	217	95 HRBW	...	
S30909	309H ^F	75	515	30	205	40	217	95 HRBW	not required	
S30909	309H ^F	75	515	30	205	40	217	95 HRBW	not required	
S30940	309Cb ^F	75	515	30	205	40	217	95 HRBW	not required	
S30941	309Hcb ^F	75	515	30	205	40	217	95 HRBW	not required	
S31008	310S	75	515	30	205	40	217	95 HRBW	not required	
S31009	310H ^F	75	515	30	205	40	217	95 HRBW	not required	
S31040	310Cb ^F	75	515	30	205	40	217	95 HRBW	not required	
S31041	310Hcb ^F	75	515	30	205	40	217	95 HRBW	not required	
S31050	310 MoLN ^F									
S31060	t ≤ 0.25 in. t > 0.25 in.	84	580	39	270	25	217	95 HRBW	not required	
S31060	...	78	540	37	255	25	217	95 HRBW	not required	
S31060	...	87	600	41	280	40	217	95 HRBW	not required	
S31254	...									
Sheet and Strip										
S31266	...	100	690	45	310	35	223	96 HRBW	not required	
S31277	...	95	655	45	310	35	223	96 HRBW	not required	
S31600	...	109	750	61	420	35	not required	
S31603	316L	112	770	52	360	40	not required	
S31609	316H	75	515	30	205	40	217	95 HRBW	not required	
S31635	316Ti ^F	70	485	25	170	40	217	95 HRBW	not required	
S31640	316Cb ^F	75	515	30	205	40	217	95 HRBW	not required	
S31640	316Cb ^F	75	515	30	205	40	217	95 HRBW	not required	
S31651	316N									
S31653	316LN	80	550	35	240	35	217	95 HRBW	not required	
S31655	...	75	515	30	205	40	217	95 HRBW	not required	
S31700	317	92	635	45	310	35	241	100 HRBW	not required	
S31703	317L	75	515	30	205	35	217	95 HRBW	not required	
S31725	317LM ^F	75	515	30	205	40	217	95 HRBW	not required	
S31726	317LMN ^F	75	515	30	205	40	217	95 HRBW	not required	
S31727	...	80	550	35	240	40	223	96 HRBW	not required	
S31730	...	80	550	36	245	35	217	96 HRBW	not required	
S31753	317LN	70	480	25	175	35	not required	
S32050	...	80	550	35	240	40	217	95 HRBW	not required	
S32050	...	98	675	48	330	40	250	...	not required	
S32053	...									
S32100	321	93	640	43	295	40	217	96 HRBW	not required	
S32109	321H	75	515	30	205	40	217	95 HRBW	not required	
S32615 ^K	...	75	515	30	205	40	217	95 HRBW	not required	
S32615 ^K	...	80	550	32	220	25	not required	



TABLE 2 Continued

UNS Designation	Type ^A	Tensile Strength, min		Yield Strength, ^B min		Elongation in 2 in. or 50 mm, min, %	Hardness, max ^C		Cold Bend ^D
		ksi	MPa	ksi	MPa		Brinell, HBW	Rockwell	
S32654	...	109	750	62	430	40	not required
S33228	...	73	500	27	185	30	95 HRBW	...	not required
S33400	334 ^F	70	485	25	170	30	92 HRBW	...	not required
S33425	...	75	515	30	205	40	not required
S33550	...	87	600	41	280	35	95 HRBW	...	not required
S34565	...	115	795	60	415	35	241	100 HRBW	not required
S34700	347	75	515	30	205	40	201	92 HRBW	not required
S34709	347H	75	515	30	205	40	201	92 HRBW	not required
S34751	347LN	75	515	30	205	40	201	92 HRBW	not required
S34800	348	75	515	30	205	40	201	92 HRBW	not required
S34809	348H	75	515	30	205	40	201	92 HRBW	not required
S35045	...	70	485	25	170	35	not required
S35115	...	85	585	40	275	40	241	100 HRBW	not required
S35125	...	70	485	30	205	35	not required
S35135	...	80	550	30	205	30	not required
Sheet and Strip	...	75	515	30	205	30	not required
Plate	...	90	620	40	275	30	241	100 HRBW	not required
S35140	...	94	650	39	270	40	217	95 HRBW	not required
S35315	...	75	515	30	205	40	217	95 HRBW	not required
S38100	XM-15 ^V	78	540	37	255	30	not required
S38815	...	100	690	65	450	25	293	31 HRC	not required
S31200	...	100	690	70	485	20	290
S31260	...	90	620	65	450	25	293	31 HRC	not required
S31803	...	90	620	65	450	25	...	25 HRC	not required
S32001	...	100	690	70	485	25	293	31 HRC	not required
S32003	...	95	655	65	450	25	293	31 HRC	not required
	t ≤ 0.187 in. [5.00 mm]	101	700	77	530	30	290	31 HRC	not required
	t > 0.187 in. [5.00 mm]	94	650	65	450	30	290	31 HRC	not required
S32101	...	94	650	65	450	30	290	31 HRC	not required
	t ≤ 0.187 in. [5.00 mm]	94	650	65	450	30	290	31 HRC	not required
	t > 0.187 in. [5.00 mm]	94	650	65	450	30	290	31 HRC	not required
S32202	...	94	650	65	450	30	290	31 HRC	not required
S32205	2205 ^F	95	655	65	450	25	293	31 HRC	not required
S32304	2304 ^F	87	600	58	400	25	290	32 HRC	not required
S32506	...	90	620	65	450	18	302	32 HRC	not required
S32520	...	112	770	80	550	25	310	32 HRC	not required
S32550	255 ^F	110	760	80	550	15	302	32 HRC	not required
S32750	2507 ^F	116	795	80	550	15	310	32 HRC	not required
S32760	...	108	750	80	550	25	310	32 HRC ^A	not required
S32808	...	101	700	72	500	15	310	32 HRC	not required
S32900	329	90	620	70	485	15	269	28 HRC	not required
S32906	...	116	800	94	650	25.0	310	32 HRC	not required
	t < 0.4 in. [10.0 mm]	109	750	80	550	25.0	310	32 HRC	not required
	t ≥ 0.4 in. [10.0 mm]	109	750	80	550	25.0	310	32 HRC	not required



TABLE 2 Continued

UNS Designation	Type ^A	Tensile Strength, min		Yield Strength, ^B min		Elongation in 2 in. or 50 mm, min, %	Hardness, max ^C		Cold Bend ^D
		ksi	MPa	ksi	MPa		Brinell, HBW	Rockwell	
S32950 ^L	...	100	690	70	485	15	293	32 HRC	not required
S39274	...	116	800	80	550	15	310	32 HRC	not required
S81921	...	90	620	65	450	25	293	31 HRC	not required
S82011	...	101	700	75	515	30	293	31 HRC	not required
	t ≤ 0.187 in. [5.00 mm]	95	655	65	450	30	293	31 HRC	not required
	t > 0.187 in. [5.00 mm]	94	650	58	400	35	290		
S82012	t > 0.187 in. [5.00 mm]	102	700	73	500	35		31 HRC	not required
S82013	...	90	620	65	450	30	293	31 ^J	not required
S82031	t > 0.187 in. [5.00 mm]	94	650	58	400	35	290		not required
	t ≤ 0.187 in. [5.00 mm]	102	700	73	500	35		31 HRC	not required
S82121	...	94	650	65	450	25	286	30 HRC	not required
S82122	t < 0.118 in. [3.00 mm]	101	700	72	500	25	290	32 HRC	not required
	t ≥ 0.118 in. [3.00 mm]	87	600	58	400	30	290	32 HRC	not required
S82441	...	107	740	78	540	25	290	31 HRC	not required
	t < 0.4 in. [10.0 mm]	99	680	70	480	25	290	31 HRC	not required
	t ≥ 0.4 in. [10.0 mm]								
S32803	...	87	600	72	500	16	241	100 HRBW	not required
S40300	403	70	485	30	205	25 ^N	217	96 HRBW	180
S40500	405	60	415	25	170	20	179	88 HRBW	180
S40900 ^M	409 ^M								
S40910	...	55	380	25	170	20	179	88 HRBW	180
S40920	...	55	380	25	170	20	179	88 HRBW	180
S40930	...	55	380	25	170	20	179	88 HRBW	180
S40945	...	55	380	30	205	22	...	80 HRBW	180
S40975	...	60	415	40	275	20	197	92 HRBW	180
S40977	...	65	450	41	280	18	180	88 HRBW	not required
S41000	410	65	450	30	205	20	217	96 HRBW	180
S41003	...	66	455	40	275	18	223	20 HRC	not required
S41008	410S	60	415	30	205	22 ^N	183	89 HRBW	180
S41045	...	55	380	30	205	22	...	80 HRBW	180
S41050	...	60	415	30	205	22	183	89 HRBW	180
S41500	...	115	795	90	620	15	302	32 HRC	not required
S42000	420	100 ^O	690 ^O	15	217	96 HRBW	not required
S42035	...	80	550	55	380	16	180	88 HRBW	not required
S42200	422	248	24 HRC	not required
S42900	429 ^F	65	450	30	205	22 ^N	183	89 HRBW	180
S43000	430	65	450	30	205	22 ^N	183	89 HRBW	180
S43035	439	60	415	30	205	22	183	89 HRBW	180



TABLE 2 Continued

UNS Designation	Type ^A	Tensile Strength, min		Yield Strength, ^B min		Elongation in 2 in. or 50 mm, min, %		Hardness, max ^C		Cold Bend ^{D,E}
		ksi	MPa	ksi	MPa	in	50 mm, min, %	Brinell, HBW	Rockwell	
S43037	...	50	360	30	205	22	22	183	89	180
S43100	431	285	29 HRC	not required
S43400	434	65	450	35	240	22	22	...	89 HRBW	180
S43600	436	65	450	35	240	22	22	...	89 HRBW	180
S43932	...	60	415	30	205	22	22	183	89 HRBW	180
S43940	...	62	430	36	250	18	18	180	88 HRBW	not required
S44330	...	56	390	30	205	22	22	187	90 HRBW	not required
S44100	...	60	414	35	241	20	20	190	90 HRBW	not required
S44200	442	65	515	40	275	20	20	217	96 HRBW	180
S44400	...	60	415	40	275	20	20	217	96 HRBW	180
S44500	...	62	427	30	205	22	22	...	83 HRBW	180
S44535	...	58	400	36	250	25 ^F	25 ^F	...	90 ^O HRBW	not required
S44536	...	60	410	35	245	20	20	192	90 HRBW	180
S44537	...	65	450	46	320	18 ^G	18 ^G	200	93 HRBW	180
S44600	446	65	515	40	275	20	20	217	96 HRBW	135
S44626	XM-33 ^J	68	470	45	310	20	20	217	96 HRBW	180
S44627	XM-27 ^J	65	450	40	275	22	22	187	90 HRBW	180
S44635	...	90	620	75	515	20	20	269	28 HRC	180
S44660	...	85	585	65	450	18	18	241	100 HRBW	180
S44700	...	80	550	60	415	20	20	223	20 HRC	180
S44725	...	65	450	40	275	20	20	210	95 HRBW	180
S44735	...	80	550	60	415	18	18	255	25 HRC	180
S44800	...	80	550	60	415	20	20	223	20 HRC	180
S46800	...	60	415	30	205	22	22	...	90 HRBW	180

^A Unless otherwise indicated, a grade designation originally assigned by the American Iron and Steel Institute (AISI).

^B Yield strength shall be determined by the offset method at 0.2 % in accordance with Test Methods and Definitions A370. Unless otherwise specified (see Specification A480/A480M, paragraph 4.1.11, Ordering Information), an alternative method of determining yield strength may be based on total extension under load of 0.5 %.

^C Either Brinell or denoted Rockwell Hardness scale is permissible. For thin materials, see Specification A480/A480M (17.2.1) and Test Methods A370 (18.1.2) on superficial testing.

^D Bend tests are not required for chromium steels (ferritic or martensitic) thicker than 1 in. [25 mm] or for any austenitic or duplex (austenitic-ferritic) stainless steels regardless of thickness.

^E Elongation for thickness, less than 0.015 in. [0.38 mm] shall be 20 % minimum, in 1 in. [25.4 mm].

^F Common name, not a trademark, widely used, not associated with any one producer.

^G Yield strength requirements shall not apply to material under 0.020 in [0.50 mm] in thickness.

^H Not applicable for thicknesses under 0.010 in. [0.25 mm].

^I Type 201 is generally produced with a chemical composition balanced for rich side (Type 201-1) or lean side (Type 201-2) austenite stability depending on the properties required for specific applications.

^J Naming system developed and applied by ASTM.

^K For S32615, the grain size as determined in accordance with the Test Methods E112, Comparison Method, Plate II, shall be No. 3 or finer.

^L Prior to Specification A240 - 89b, the tensile value for S32950 was 90 ksi.

^M S40900 (Type 409) has been replaced by S40910, S40920, and S40930. Unless otherwise specified in the ordering information, an order specifying S40900 or Type 409 shall be satisfied by any one of S40910, S40920, or S40930 at the option of the seller. Material meeting the requirements of S40910, S40920, or S40930, may at the option of the manufacturer be certified as S40900.

^N Material 0.050 in [1.27 mm] and under in thickness shall have a minimum elongation of 20 %.

^O Hardness is required to be provided for information only, but is not required to meet a particular requirement.

^P The minimum elongation for plates thicker than 0.630 in. (16 mm) shall be 8 %.

^Q Maximum. Type 420 is usually used in the heat-treated condition (quenched and tempered to a specific range of hardness or tensile strength).

^R Hardness conversion tables for superduplex stainless steels do not exist in ASTM E140. The conversion value from HBW to HRC has been added to maintain consistency with other ASTM standards for these superduplex stainless steels.

SUPPLEMENTARY REQUIREMENTS

A supplementary requirement shall apply only when specified in the purchase order.

S1. Charpy Impact Testing of Plate

S1.1 Charpy impact tests shall be conducted in accordance with Test Methods and Definitions **A370**.

S1.2 *Number of Tests*—One impact test (three specimens) shall be made from one plate per heat treatment lot in the final heat treated condition.

S1.3 *Orientation of Test Specimens*—Unless specified as transverse specimens (long axis of the specimen transverse to the final rolling direction, root of the notch perpendicular to the rolling face) on the purchase order, the orientation of the specimens shall be longitudinal (long axis of the specimen parallel to the final rolling direction, root of the notch perpendicular to the rolling face). The manufacturer is permitted to test transverse specimens provided that such tests meet the acceptance criteria applicable to longitudinal specimens. Unless otherwise specified on the purchase order, the specimens shall be taken so as to include the mid-thickness of the product.

S1.4 *Test Temperature*—The purchaser shall specify the test temperature. The manufacturer is permitted to test specimens at a temperature lower than that specified by the purchaser, provided that such tests shall meet the acceptance criteria applicable to specimens tested at the specified temperature (see the note below).

NOTE S1.1—Test Methods **A923**, Method B, applicable to some duplex (austenitic-ferritic) stainless steels as listed in Test Methods **A923**, uses a Charpy impact test for the purpose of determining the absence of detrimental intermetallic phases. Method B specifies a test temperature and acceptance criterion, expressed as impact energy, for each type of steel covered. It may be economical for the Charpy impact tests performed on duplex stainless steels covered in both Specification A240 and Test Methods **A923** to be performed at the lower of the temperatures specified by this supplementary requirement and Test Methods **A923** Method B, with measurement of both lateral expansion and impact energy.

S1.5 *Acceptance Limit*—Unless otherwise specified on the purchase order, each of the three specimens tested shall show a lateral expansion opposite the notch of not less than 0.015 in. [0.38 mm].

S1.6 *Records*—The recorded results shall include the specimen orientation, specimen size, test temperature, absorbed energy values (if required), and lateral expansion opposite the notch.

S2. Materials for High-Temperature Service

S2.1 Unless an H grade has been ordered, this supplementary requirement shall be specified for ASME Code applications for service above 1000°F [540°C].

S2.2 The user is permitted to use an austenitic stainless steel as the corresponding H grade when the material meets all requirements of the H grade including chemistry, annealing temperature, and grain size (see Section 6).

S2.3 The user is permitted to use an L grade austenitic stainless steel for service above 1000°F [540°C], subject to the applicable allowable stress table of the ASME Code, when the material meets all requirements of this specification and the grain size is ASTM No. 7 or coarser as determined in accordance with Test Methods **E112**. The grain size shall be reported on a Certified Test Report.

S3. One Percent Offset Yield Strength

S3.1 If reporting of 1 % offset yield strength is specified on the purchase order; the material shall meet the strength requirements shown in **Table S3.1**.

S3.2 The mechanical properties, including 1 % offset yield strength and all other required properties shall be reported on a Material Test Report.

TABLE S3.1 Tensile and Yield Strength Requirements

NOTE 1—These values apply only for material of 1.5 inches (38 mm) nominal thickness or less.

UNS	Grade	Tensile Strength, min., Ksi [MPa]	0.2 % Offset Yield Strength, Min., Ksi [MPa]	1 % Offset Yield Strength, Min., Ksi [MPa]
S31603	316L	70 [485]	25 [170]	38 [260]
S31600	316	75 [515]	30 [205]	38 [260]
S31653	316LN	75 [515]	30 [205]	46 [320]
S30403	304L	70 [485]	25 [170]	35 [240]
S30400	304	75 [515]	30 [205]	36 [250]
S30453	304LN	75 [515]	30 [205]	45 [310]
S30451	304N	80 [550]	35 [240]	45 [310]
S32100	321	75 [515]	30 [205]	35 [240]

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A240/A240M – 16a) that may impact the use of this standard. (Approved Nov. 1, 2017.)

- (1) Added new 5.3.
- (2) Added Supplementary Requirement S3 on 1 % Offset Yield Strength.

Committee A01 has identified the location of selected changes to this standard since the last issue (A240/A240M – 16) that may impact the use of this standard. (Approved Dec. 1, 2016.)

- (1) Added grade UNS S30616 to **Tables 1 and 2**.

Committee A01 has identified the location of selected changes to this standard since the last issue (A240/A240M – 15b) that may impact the use of this standard. (Approved May 1, 2016.)

- (1) Increased maximum hardness in **Table 2** for UNS S32760 to 310 HBW (32 HRC) and added footnote.
- (2) Corrected Ni range for S38815 in **Table 1**.

Committee A01 has identified the location of selected changes to this standard since the last issue (A240/A240M – 15a) that may impact the use of this standard. (Approved Nov. 1, 2015.)

- (1) Added grade UNS S82013 to **Tables 1 and 2**.
- (2) Added grade UNS S43037 to **Tables 1 and 2**.

Committee A01 has identified the location of selected changes to this standard since the last issue (A240/A240M – 15) that may impact the use of this standard. (Approved March 1, 2015.)

- (1) Added “including architectural and aesthetic applications to” Scope subsection 1.1.
- (2) Added *architectural*, *building*, and *construction* to Key-words.
- (3) Added grade UNS S31655 added to **Tables 1 and 2**.

Committee A01 has identified the location of selected changes to this standard since the last issue (A240/A240M – 14) that may impact the use of this standard. (Approved Jan. 1, 2015.)

- (1) S31730 added to **Tables 1 and 2**.
- (2) Footnote A of **Table 1** revised to explain ellipses.
- (3) Altered Column head for Rockwell Hardness from “Rockwell B” to “Rockwell” in **Table 2**.

(4) Added the appropriate Rockwell Scale designation to all applicable maximums in the Rockwell Column in **Table 2**.

(5) Eliminated footnote *J* of **Table 2**, which designated certain hardness maximums as HRC, as it is no longer necessary.

(6) Modified footnote *C* of **Table 2**, to permit the denoted Rockwell Hardness Scales and to permit the use of superficial scales for thin materials.

(7) Added grades UNS S40300, S42000, S42200, S43100, S44200, and S44600 from A176 to **Tables 1 and 2**.

(8) Added footnote *Q* to **Table 2** (identical to footnote *E* from A176, Table 2).

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>