

TEST REPORT

No.: SZIN1601000054PS

Date: Jan 18, 2016

Page: 1 of 3

CUSTOMER NAME:

LIVART MARINE INDUSTRY CO.,LTD

ADDRESS:

26E, DAQING BUILDING, SHENNAN BOULEVARD, FUTIAN DISTRICT,

SHENZHEN, GUANGDONG, CHINA.

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name

: FROTH

SGS Ref. No.

: GZIN1601000431MR

Date of Receipt

: Jan 04, 2016

Testing Start Date

: Jan 04, 2016

Testing End Date

: Jan 18, 2016

Test result(s)

: For further details, please refer to the following page(s)

Signed for SGS-CSTC Standards Technical Services Co., Ltd. Shenzhen Branch Testing Center

Ramber Li

Authorized signatory





TEST REPORT

No.: SZIN1601000054PS

Date: Jan 18, 2016

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion	
1	Water Absorption	ASTM D2842-12 Method B	2.51 %	/	


Note:

Pass: Meet the requirements;

Fail: Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:





This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions ferms-en-Documents on the imitation of it ability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that intomation contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Cleint's instructions, if any, The Company and the company is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and object the standard alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) lested and such sample(s) are retained for 30 days only.



TEST REPORT

No.: SZIN1601000054PS

Date: Jan 18, 2016

Page: 3 of 3

Test Item: Water Absorption Sample Description: See photo

Test Method: ASTM D2842-12 Method B

Test Condition:

Specimen: 148 mm×146 mm×74 mm

Drying condition: 50±2 ℃, to constant mass

Immersion condition: 23±2 °C, 96 h

Lab Environmental Condition: 23±2 ℃, 50±5 % RH


Test Result:

Test Item	Test Result	
Water Absorption	2.51 %	

Note: 1. Test specimens were cut from the sample.

2. The above test was carried out by a SGS laboratory.

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Oven	UFE600A0E3	GZMR-PL-E101	2015-11-18	2016-11-17
Electron Balance	JJ8000A	GZMR-PL-E079	2015-02-11	2016-02-10

****** End of report*****



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or access at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx, Attention is a drawn to the limitation of its indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon ref the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole respons is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations unde transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthor alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fix extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s retained for 30 days only.

SSS Bldg, No. 4 Jianghao Industrial Park, No. 430 Jihua Road, Barillan , Longgang District, Shenzhen, China 518129 t (86–755) 25328282 f (86–755) 83197625 www.sgsgroup.com.cn 中国·深圳·龙岗区坂田吉华路430号江澗工业园4栋SGS大楼 邮编: 518129 t (86-755) 25328282 f (86-755) 83197625 e sgs.china@sgs.com