

PERFORMANCE

REFLECTIVE FLOAT GLASS

OPTICAL PARAMETER

NOVAL GLASS GROUP LTD

E-mail: info@novalglass.com

Tel: +86-532-82751111

Fax: +86-532-82755222

Add: No.33 Shandong Rd, Qingdao, China

REFLECTIVE FLOAT GLASS OPTICAL PARAMETER

Glass	Visible Light		Sunlight		Shading Co-efficient (SC)	Sum of Transmittance of Solar Energy (%)
	Transmittance (%)	Reflectance (%)	Direct Transmittance (%)	Direct Reflectance (%)		
5mm F-Green Reflective	31.12	34.80	25.49	19.61	0.45	39.65
6mm F-Green Reflective	29.94	33.72	21.12	18.92	0.41	36.59
4mm Pink Reflective	30.66	36.06	47.82	29.17	0.60	53.76
6mm Pink Reflective	29.92	28.64	46.40	22.14	0.61	54.52
4mm Dark Blue Reflective	25.62	13.98	39.36	16.47	0.57	50.76
5mm Dark Blue Reflective	20.92	12.52	33.42	15.00	0.53	46.73
6mm Dark Blue Reflective	13.42	13.68	25.52	16.81	0.45	40.40
5mm Ford Blue Reflective	27.50	19.38	37.07	16.56	0.55	49.03
6mm Ford Blue Reflective	24.97	16.51	32.04	14.72	0.51	45.78
4mm Euro Grey Reflective	26.90	19.59	37.38	17.36	0.55	49.05
6mm Euro Grey Reflective	19.55	13.99	27.64	12.69	0.48	42.97
4mm Dark Grey Reflective	17.96	10.10	30.09	11.30	0.51	45.21
5mm Dark Grey Reflective	14.03	9.07	25.06	10.56	0.47	42.05
6mm Dark Grey Reflective	13.02	6.97	22.70	8.20	0.46	40.53