

LUPOL GP3400

Injection Molding, PP+MF40%

Description

General Purpose

Application

Electrical & Electronic, Automotive Parts

| Properties | Test Condition | Test Method | Unit | Typical Value |
|---|----------------|-------------|--------------------|---------------|
| Physical | | | | |
| Specific Gravity | | ASTM D792 | - | 1.2 |
| Molding Shrinkage (Flow), 3.2mm | | ASTM D955 | % | 0.6~1.1 |
| Melt Flow Rate | 230 °C/2.16kg | ASTM D1238 | g/10min | 10 |
| Mechanical | | | | |
| Tensile Strength, 3.2mm | | ASTM D638 | | |
| @ Yield | 5mm/min | | kg/cm ² | 340 |
| Tensile Elongation, 3.2mm | | ASTM D638 | | |
| @ Yield | 5mm/min | | % | - |
| @ Break | 5mm/min | | % | 10.0 |
| Flexural Strength, 6.4mm | 1.3mm/min | ASTM D790 | kg/cm ² | 570 |
| Flexural Modulus, 6.4mm | 1.3mm/min | ASTM D790 | kg/cm ² | 44,000 |
| IZOD Impact Strength, 6.4mm (Notched) | | ASTM D256 | | |
| | 23 °C | | kg·cm/cm | 2.5 |
| | -10 °C | | kg·cm/cm | |
| Rockwell Hardness | R-Scale | ASTM D785 | - | - |
| Thermal | | | | |
| Heat Deflection Temperature, 3.2mm (Unannealed) | | ASTM D648 | | |
| | 4.6kg | | °C | 140 |

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Updated : 9-Nov-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUPOL GP3400

Injection Molding, PP+MF40%

Description

General Purpose

Application

Electrical & Electronic, Automotive Parts

Processing Guide (Injection Molding)

| Processing Parameters | | Unit | Value |
|--------------------------|--------|--------------------|-----------|
| Drying Temperature | | °C | 70 ~ 80 |
| Drying Time | | hrs | 3 ~ 4 |
| Minimum Moisture Content | | % | 0.01 |
| Melt Temperature | | °C | 200 ~ 230 |
| Cylinder Temperature | Rear | °C | 190 ~ 210 |
| | Middle | °C | 200 ~ 230 |
| | Front | °C | 200 ~ 230 |
| Nozzle Temperature | | °C | 210 ~ 230 |
| Mold Temperature | | °C | 40 ~ 60 |
| Back Pressure | | kg/cm ² | 300 ~ 600 |
| Screw Speed | | rpm | 30 ~ 60 |

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated : 9-Nov-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.