

LUPOY GN1002FH

Injection Molding, PC

Description

Halogen Free Flame Retardant, Heat Resistant
Chemical Resistance, High Impact

Application

IT/OA Housing and Components (Adaptor)

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ASTM D792	-	1.2
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	0.5~0.8
Melt Flow Rate	300°C/1.2kg	ASTM D1238	g/10min	13
Mechanical				
Tensile Strength, 3.2mm		ASTM D638		
@ Yield	50mm/min		kg/cm ²	630
Tensile Elongation, 3.2mm		ASTM D638		
@ Yield	50mm/min		%	
@ Break	50mm/min		%	100
Tensile Modulus, 3.2mm	1mm/min	ASTM D638	kg/cm ²	
Flexural Strength, 3.2mm	10mm/min	ASTM D790	kg/cm ²	980
Flexural Modulus, 3.2mm	10mm/min	ASTM D790	kg/cm ²	25,000
IZOD Impact Strength, 3.2mm (Notched)		ASTM D256		
	23°C		kg·cm/cm	75
	-30°C		kg·cm/cm	12
Rockwell Hardness	R-Scale	ASTM D785	-	
Thermal				
Heat Deflection Temperature, 6.4mm (Unannealed)		ASTM D648		
	18.6kg		°C	121
	4.6kg		°C	
Vicat Softening Temperature		ASTM D1525		
	5kg, 120°C/h		°C	135
Flammability		UL94		
0.7mm			class	
1.5mm			class	V-0
2.0mm			class	V-0, 5VB
3.2mm			class	
Relative Temperature Index		UL 746B		
Electrical			°C	80
Mechanical with Impact			°C	80
Mechanical without Impact			°C	80

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Updated : Nov-09, 2009

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUPOY GN1002FH

Injection Molding, PC

Description

Halogen Free Flame Retardant, Heat Resistant
Chemical Resistance, High Impact

Application

IT/OA Housing and Components (Adaptor)

Electrical

Comparative Tracking Index(CTI)	Solution A	IEC 60112	Volts
Surface Resistivity		IEC 60093	Ohm
Volume Resistivity	23 °C	ASTM D257	Ohm·m
Arc Resistance	23 °C	ASTM D495	Ohm·cm
Dielectric Strength, 1mm	23 °C	ASTM D149	kV/mm
Dielectric Constant (10 ⁶ Hz)	23 °C	ASTM D150	sec

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molulded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Processing Guide (Injection Molding)

Processing Parameters		Unit	Value
Drying Temperature		°C	90~100
Drying Time		hrs	3 ~ 4
Minimum Moisture Content		%	0.02
Melt Temperature		°C	275 ~ 290
Cylinder Temperature	Rear	°C	270 ~ 285
	Middle	°C	275 ~ 290
	Front	°C	275 ~ 290
Nozzle Temperature		°C	270 ~ 285
Mold Temperature		°C	80 ~ 100
Back Pressure		kg/cm ²	20
Screw Speed		rpm	40 ~ 80

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.